

## ABSTRACT

A green sheet coating material includes ceramic  
5 powder and a binder resin containing a butyral based  
resin as the main component, which furthermore includes a  
xylene based resin as a tackifier. The xylene based resin  
is included in a range of 1.0 wt% or less, more  
preferably 0.1 or more and 1.0 wt% or less, and  
10 particularly preferably more than 0.1 and 1.0 wt% or less  
with respect to 100 parts by weight of ceramic powder.